

TECHNICAL DATA SHEET

Bonndeco Anti-Rust Primer

Modified Acrylic Resin and anti-rust pigment filler

Product Description

Bonndeco Anti-Rust Primer is made of water-based acrylic resin, anti-rust pigment filler and additives. It has excellent anti-rust ability, good adhesion and anti-corrosion properties. This is water based, free of benzene, toluene, free TDI and other carcinogens and harmful heavy metals, no irritating odor as well as healthy and environmentally friendly.

Features & Benefits

- Extremely resistant to flash rust
- Excellent water resistance, rust and corrosion resistance
- Good adhesion
- Simple application and fast drying
- Non-toxic and tasteless, no explode, safe and environmentally friendly products.

Properties	
Condition in container	There shall be no lumps, no separation and no coagulation of the ingredients
Low temperature stability @-5℃	Unchanged
Impact Resistant/cm	<40
Bending/mm	2
Cross-cut	<1
Water Resistant	24 hours, No peeling, No rust

Application Substrate

It is widely used in rust prevention and various steel structures, mechanical equipment, petroleum tanks and cast iron parts.

Application

Roller, Spray, Brush, Airless

Color

White

Package available

4kg/can or 20kg/can

Thinning ratio

5 ~ 10%

Drying time

- Touch Dry: 2 hours
- Recoat: 4 hours
- Fully Dry: 7 days
- (25℃, 70% RH)

Theoretical spreading ratio

Approximately 30-40m2/coat/4can
Approximately 150-200m2/coat/20can
(According to substrate condition)

Remarks:-

- The recommended coverage rates, including those of normal wastage, are for reference only. Actual coverage may vary depending on the working condition of the site, the degree of evenness and smoothness of the substrate surface, and the pattern of the texture sample as selected and approved by the architect or client.
- We reserve the right to change or adjust the composition of material used in the specification of our products due to our constant research and development to improve of the quality of our products.

TECHNICAL DATA SHEET

Bonndeco Anti-Rust Primer

Modified Acrylic Resin and anti-rust pigment filler

Surface Preparation

Performance of rust prevention by paint depends on the elaboration of substrate preparation to the metal surface. Surface preparation is the most important process and painting durability is also influenced. Therefore, consideration is needed. Each painting's anticorrosive, wet ability, drying time and other painting relation also depends on the suitability to the substrate. Consideration is needed for substrate preparation from application itself. The level of substrate preparation desirable to high level than minimum level requested. The method and level of substrate preparation written in application is on below.

Type of Surface Preparation		
Preparation Type	ISO Standard	Surface Preparation
Blast Cleaning	Sa2 1/2	New: Prepare to metal color uniformly after removing the mill scale, rust, paint, oil and fats Renovation: Prepare the substrate to ash gray color uniformly and remove the deteriorated film and rust.
Power tools cleaning	St3	Remove deteriorated film and rust manually or by powered tools (electric sander grinder, scraper, wire, wheels, etc.) then expose the steel
Hand tools or Power tools Cleaning	St2	Remove deteriorated film and rust manually or by powered tools (electric sander grinder, scraper, wire, wheels, etc.) Scape the rust generated portions until the steel exposed.

Application Procedure

- Shake and stir thoroughly to get a complete dispersion of pigment.
- Use standard practice, either by rolling, brush or spraying, to ensure conformance to the specification requirement.
- Workers, applying in confined areas, are required to wear protection masks and exhaust ventilation should be properly supplied to the confined area.

Precautions in use

Handling and storage

- Do not use near flames
- All workplaces to always have specific ventilating equipment in operation.
- Particular precautions to be taken for good ventilation during application and while drying, and precautions taken to avoid any inhaling of fumes.
- During handling, precautions to be taken to avoid any skin contact and as necessary, gas mask against organic gas or fresh air supplying masks to be worn and also use head towels, wear protective eyeglasses, long sleeved protective gowns, neck protecting towels, protective gloves, etc.
- When coat is spilled, wipe with waste cloths to be kept stored in water filled containers.
- Until final disposal, all waste cloths that have been exposed to coat, hardeners or thinners, and leftover coat, spray dust, etc. for disposal shall be kept doused in water filled containers.
- After handling or application, hands to be thoroughly washed and extensive gargling is advised.
- The handles on the upper part of the tin containers are solely for carrying the tins. Please do not use ropes and hooks on the handles for hanging the tins.
- During storage, containers are to be tightly sealed and stored out of any direct sunlight or any exposure to rain, in a cool, well ventilated area.
- Please store away from any foreign instruction by third parties and out of the reach of children.

Remarks:-

1. The recommended coverage rates, including those of normal wastage, are for reference only. Actual coverage may vary depending on the working condition of the site, the degree of evenness and smoothness of the substrate surface, and the pattern of the texture sample as selected and approved by the architect or client.
2. We reserve the right to change or adjust the composition of material used in the specification of our products due to our constant research and development to improve of the quality of our products.